



# TRENDY TILES

## LONDON

### MONOKINI MEDITERRANEO







# TRENDY TILES

## LONDON

MONOKINI

MEDITERRANEO

Nominal values size 7,5x30 cm

### MATT 7.5x30 cm

ARCTIC WHITE



Matt finished: MKI-AW-M

LONDON GREY




Matt finished: MKI-LG-M

ARIZONA TAN




Matt finished: MKI-AT-M

BELUGA



Matt finished: MKI-BL-M

TROCADERO BROWN



Matt finished: MKI-TB-M

### CRAQUELÉ 7.5x30 cm

ARCTIC WHITE



Craquelé finished: MKI-AW-CR

MEDITERRANEAN SEA



Craquelé finished: MKI-MS-CR

LONDON GREY



Craquelé finished: MKI-LG-CR

COTSWOLDS



Craquelé finished: MKI-CT-CR

### GLOSSY 7.5x30 cm

ARCTIC WHITE



Glossy finished: MKI-AW-GL

LONDON GREY



Glossy finished: MKI-LG-GL

ARIZONA TAN



Glossy finished: MKI-AT-GL

BELUGA



Glossy finished: MKI-BL-GL

TROCADERO BROWN



Glossy finished: MKI-TB-GL



# Packaging Details

Nominal values

			CM	KG	BOXES	PCS/BOX	MQ/PALLET	KG/BOX
MEDITERRANEO		1 pallet	7,5x30	626,00	80	22	40,00	7,45

TECHNICAL CHARACTERISTICS	REFERENCE STANDARD		REQUIRED VALUE		VALUE
WATER ABSORPTION (E)	ASTM C373		7% < e ≤ 20%		COMPLIANT
BREAKING STRENGTH (S)	ASTM C648		≥ 125 LBF		≥ 125 LBF
LINEAR THERMAL EXPANSION	ASTM C372		NO PROVISION		$\alpha \leq 8 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$ $\alpha \leq 4.4 \times 10^{-6} \text{ }^{\circ}\text{F}^{-1}$
THERMAL SHOCK RESISTANCE	ASTM C484		NO ALTERATIONS		RESISTANT
CRAZING RESISTANCE	ASTM C424		NO ALTERATIONS		RESISTANT
CHEMICAL RESISTANCE	ASTM C650		AS INDICATED BY MANUFACTURER		RESISTANT
STAIN RESISTANCE	ASTM C1378		NO PROVISION		RESISTANT
LEAD AND CADMIUM GIVEN OFF	ASTM C895		NO PROVISION		RESISTANT
FROST RESISTANCE	ASTM C1026		NO PROVISION		NOT RESISTANT
BOND STRENGTH	ASTM C482		≥ 50 PSI		CONFORMS
DIMENSIONS	EDGE WARPAGE	ASTM C485	RECTIFIED - 0.30% / + 0.40% OR MAX - 0.04" / +0.05"	CALIBRATED - 0.30% / + 0.40% OR MAX - 0.04" / +0.05"	COMPLIANT
	DIAGONAL WARPAGE	ASTM C485	RECTIFIED - 0.30% / + 0.40% OR MAX - 0.05" / +0.07"	CALIBRATED - 0.30% / + 0.40% OR MAX - 0.05" / +0.07"	COMPLIANT
	NOMINAL DIMENSIONS	ASTM C499	RECTIFIED ±2.0% OF NOMINAL DIMENSIONS	CALIBRATED ±2.0% OF NOMINAL DIMENSIONS	± 1.0%
	CALIBER RANGE	ASTM C499	RECTIFIED ± 0.25% OR MAX ± 0.03"	CALIBRATED ± 0.30% OR MAX ± 0.04"	COMPLIANT
	THICKNESS	ASTM C499	≤ 0.031"	≤ 0.031"	COMPLIANT
	WEDGING	ASTM C502	RECTIFIED ± 0.25% OR MAX ± 0.03"	CALIBRATED ± 0.40% OR MAX ± 0.05"	COMPLIANT

GL: Single- ired tile

EXCLUDING HYDROFLUORIC ACID AND ITS DERIVATIVES

As far as the craquele effect is concerned, the following details and steps must be known;

- We sell the product with a treatment already applied which helps protect it when laying,
- Once laid and grouted, the material should be washed with a sponge and warm water and in doing so the protective wax comes off from the surface but not from inside the crequelè, the treatment will last several years.



TRENDY TILES LTD

[london@trendytiles.com](mailto:london@trendytiles.com) - [trendytiles.com](http://trendytiles.com)